

CLAIMS

We claim:

1. A component comprising:
5 a silicon-based component, said silicon-based component being subject to a corrosive environment;
said silicon-based component having a rare earth silicate coating thereon; and
10 said coating having a pre-established thickness, said pre-established thickness being in the range of about 1.0 microns and 5.0 microns.
2. A component as in claim 1, wherein said
15 silicon-based component is silicon nitride.
3. A component as in claim 1, wherein said silicon-based component is silicon carbide.
- 20 4. A component as in claim 1, wherein said silicon-based component is molybdenum disilicide.
- ~~5. A component as in claim 1, wherein said
rare earth silicate coating is ytterbium silicate.~~
- 25 6. A component as in claim 1, wherein said rare earth silicate coating is lanthanum silicate.
7. A component as in claim 1, wherein said
30 rare earth silicate coating is yttrium silicate.

~~8. A component as in claim 1, wherein said pre-established thickness being in the range of about 4.0 and 5.0 microns.~~

5 9. A component as in claim 1, wherein said silicon-based component is an engine component.

~~10. A component as in claim 1, wherein said silicon-based component is a glow plug.~~

10

11. A component as in claim 1, wherein said silicon-based engine component is a turbocharger.

12. A component as in claim 1, wherein said
15 silicon-based engine component is a turbine blade.

13. A process for coating a silicon-based component, comprising:

forming a silicon-based component, wherein
20 said silicon-based component is a rare earth-doped ceramic;

increasing the temperature of said silicon-based component to about above 1100 degrees C for a time in the range of about six hours to about twelve
25 hours to oxidize said silicon-based engine component;

forming a silica layer;

reacting said rare earth-doped silicon-based ceramic of said silicon-based component by creating a reaction with the silica layer of said silicon-based
30 component;

forming a rare earth silicate coating on
said silicon-based component.

14. A silicon-based glow plug having a
5 heating element and having a tip, said tip having an
outer surface, comprising:
said silicon-based glow plug having a rare
earth silicate coating on said outer surface; and
said coating having a pre-established
10 thickness, said pre-established thickness being in the
range of about 1.0 microns and 5.0 microns.

add a1
Add B1